



PLUS[®] improves fresh-concrete rheology and hardened-concrete quality. Its polycarboxylate-ether superplasticizer reduces the water-cement ratio, while silica fume increases concrete density and resistance to chloride and sulfate ingress. Polypropylene fibers help control hairline cracking and improve impact and abrasion resistance.

Applications

- Highly durable, impermeable concrete
- High-strength, abrasion-resistant concrete
- Concrete production in hot weather
- Long-distance concrete transport, particularly in hot weather
- Hydraulic structures along the Persian Gulf
- Bridges, jetties, tanks, treatment plants and other hydraulic and marine structures
- Thin concrete sections
- Polymer tiles, cement plaster and artificial stone
- Concrete resistant to explosion and nuclear radiation
- Industrial floors, runway ramps and airport aprons
- Concrete exposed to sulfate and chloride ions

Approvals / Standards

- ASTM C1202
- BS 1881-122
- INSO 2930
- BS EN 12390-8

Advantages / Benefits

- Reduces the concrete water-cement ratio
- Improves rheology and pumpability
- Increases abrasion and compressive strength
- Reduces alkali-aggregate reaction (AAR)
- Extends concrete setting time
- Produces a smooth finish on exposed concrete
- Supports economical mix designs exposed to impact, dynamic loading, sulfate and chloride attack

Guideline for Use

Add PLUS after all concrete constituents have been fully mixed and continue mixing until homogeneous, either at the batching plant or in the truck mixer at the site. Alternatively, blend it with part or all of the mixing water during concrete production.

Dosage

3 to 6% by weight of cementitious materials. Determine the exact dosage through site trials. Production of special concrete or any dosage change requires consultation with RAMKA technical specialists.

Storage

+10°C to +30°C; store in dry conditions away from direct sunlight.

Packaging

22 kg pail

Shelf Life

1 year from the date of production in the original packaging.

Health and Safety

- Do not swallow and avoid contact with the eyes.
- In case of accidental contact with the skin or eyes, rinse immediately with plenty of fresh water.
- Non-flammable.

Basis Of Data

Product Information

chemical_base	Polycarboxylate ether and silica fume
additional_component	Polypropylene fibers
density	1.45±0.05 g/cm ³
chloride_ion	None



RAMKA

CONSTRUCCION CHEMICALS

Tel: (+98)2533557596

Mail : info@Ramkaco.com

1th Floor, Loghman St., Qom, Iran

www.RamkaCo.com

Important Notes: The information, and, in particular, the recommendations relating to the application and end-use of RAMKA products, are given in good faith based on RAMKA's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with RAMKA's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. RAMKA reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.