

MICRO[®]

Silica Fume Gel



RAMKA
CONSTRUCTION
CHEMICALS

MICRO[®] is a silica-fume slurry for improving concrete durability and reducing permeability. Silica fume densifies the concrete matrix, improves resistance to chloride and sulfate ingress, and significantly increases compressive, flexural and tensile strength.

Applications

- High-strength concrete (HSC)
- High-performance concrete (HPC)
- Shotcrete
- Self-compacting concrete
- Repair concrete
- Watertight, low-permeability concrete
- Low-heat mass concrete
- Abrasion-resistant concrete for decks, floors, overlays and dam spillways
- Blast-resistant concrete
- Concrete requiring low electrical conductivity and high electrical resistivity

Approvals / Standards

- ACI PRC 234-06
- ASTM C1240
- ASTM C1202
- BS 1881-122
- INSO 2930
- BS EN 12390-8

Guideline for Use

At the batching plant, mix MICRO with aggregate and approximately 75% of the mixing water for 1 minute, add cement and mix for 1 minute, then add the remaining water and other admixtures and continue mixing for 7 minutes. For limited ready-mixed volumes, add MICRO to the truck mixer at the site and mix at high speed for 7 minutes. A plasticizer is recommended for improved dispersion.

Dosage

3 to 16% by weight of cement, depending on project requirements and concrete application. For special projects the dosage may be increased to 25% by weight of cement. Any change outside the permitted range, or simultaneous use with other admixtures, requires RAMKA technical approval.

Storage

+10°C to +30°C; store in dry conditions away from direct sunlight.

Packaging

20 kg pail

Shelf Life

1 year from the date of production in the original packaging.

Health and Safety

- Do not swallow and avoid contact with the eyes.
- In case of accidental contact with the skin or eyes, rinse immediately with plenty of fresh water.
- Refer to the Material Safety Data Sheet (MSDS).
- Non-flammable.

Basis Of Data

Product Information

Chemical base	Silica fume
density	1.45±0.05 g/cm ³
Chloride ion	None

Advantages / Benefits

- Reduces cement content
- Increases modulus of elasticity
- Reduces permeability
- Improves resistance to alkali-silica reaction (ASR)
- Facilitates pumping and reduces wear on placing equipment
- Increases electrical resistivity and abrasion resistance
- Reduces cracking compared with dry-powder silica-fume addition
- Improves durability
- Can be used with different plasticizers
- Helps prevent thermal-stress cracking
- Improves resistance to chloride and sulfate ions
- Helps protect reinforcement and steel plates against corrosion



RAMKA

CONSTRUCTION CHEMICALS

Tel: (+98)2533557596

Mail : info@Ramkaco.com

1st Floor, Loghman St., Qom, Iran

www.RamkaCo.com

Important Notes: The information, and, in particular, the recommendations relating to the application and end-use of RAMKA products, are given in good faith based on RAMKA's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with RAMKA's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. RAMKA reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.